

ISO/IEC 17025 Certified Third Party Test Report

DATE: April 5, 2019

FILE: CLEANB.A040319A

CLIENT: CleanBrands, LLC
240 Bald Hill Road
Warwick, RI 02886

ATTN: Samantha Bendik

SAMPLE IDENTIFIED BY CLIENT AS:

Pillowcase Submitted
Manufacturer: Protect A Bed
Name: Protect A Bed AllerZip Smooth Mattress Encasement
Color White

RED LABEL SERVICE

TEST PROCEDURE:

TEST RESULTS:

**WATER VAPOR TRANSMISSION
(ASTM E96) - PROCEDURE BW:
INVERTED WATER METHOD,
73.4 °F 50% Rh, AIR GAP 3/4":**


TRANSMISSION RATE:

-	SPECIMEN 1:	3650 g/sq meter/24 hrs
-	SPECIMEN 2:	2730 g/sq meter/24 hrs
-	SPECIMEN 3:	<u>3063 g/sq meter/24 hrs</u>
		3148 g/sq meter/24 hrs average

Signed For The Company By


Joseph Lin
Laboratory Manager




Stacy Sadowy
Quality Assurance Manager

JG/04

ISO/IEC 17025 Certified Third Party Test Report

DATE: April 5, 2019

FILE: CLEANB.A040319B

CLIENT: CleanBrands, LLC
240 Bald Hill Road
Warwick, RI 02886

ATTN: Samantha Bendik

SAMPLE IDENTIFIED BY CLIENT AS:

Mattress Encasement Submitted
Manufacturer: Mattress Safe
Name: Mattress Safe Soft Cover Ultimate Mattress Encasement
Color White

RED LABEL SERVICE

TEST PROCEDURE:


TEST RESULTS:

**WATER VAPOR TRANSMISSION
(ASTM E96) - PROCEDURE BW:
INVERTED WATER METHOD,
73.4 °F 50% Rh, AIR GAP 3/4":**


TRANSMISSION RATE:

-	SPECIMEN 1:	3340 g/sq meter/24 hrs
-	SPECIMEN 2:	4557 g/sq meter/24 hrs
-	SPECIMEN 3:	<u>3080 g/sq meter/24 hrs</u>
		3659 g/sq meter/24 hrs average

Signed For The Company By


Joseph Lin
Laboratory Manager




Stacy Sadowy
Quality Assurance Manager

JG/04