

Quality Assurance & Compliance Testing Utilizing Textile & Related Technologies

19 West 36th Street, 10th Floor New York, NY 10018 Tel: 212 947 8391 Fax: 212 947 8719

FILE: CLEANB.A040620B

ATTN: Andrew Walters

www.vartest.com

# ISO/ICC 17025 Certified Third Party Test Report

DATE ISSUED:

April 7, 2020

DATE REVISED:

April 9, 2020

CLIENT:

CleanBrands, LLC

501 Centerville Road, Ste 203

Warwick, RI 02886

## SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted

Manufacturer: CleanBrands Name: CleanRest PRO Max

Style: MicronOne B: Waterproof Breathable Sleep Surface Fabric

Color Optic White

DOUBLE RED LABEL

### TEST PROCEDURES:

#### TEST RESULTS:

WATER AGAINST FACE OF FABRIC

0.25 g average water penetration

HYDROSTATIC PRESSURE TEST OPTION 2: HYDROSTATIC HEAD TESTER (AATCC 127):

Specimen 1: 7415.4 mm
Specimen 2: 6946.2 mm
Specimen 3: 6752.4 mm
Specimen 4: 6864.6 mm
Specimen 5: 7425.6 mm
Average: 7080.8 mm

RESISTANCE OF MATERIALS IN PROTECTIVE CLOTHING TO PENETRATION BY SYNTHETIC BLOOD (ASTM F1670-B):

Sample	Result	
В	Pass	

COMMENT: Uniform results in triplicate.



Quality Assurance & Compliance Testing Utilizing Textile & Related Technologies

19 West 36th Street, 10th Floor New York, NY 10018 Tel: 212 947 8391 Fax: 212 947 8719

www.vartest.com

# ISO/ICC 17025 Certified Third Party Test Report

FILE: CLEANB.A040620B

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted

Manufacturer: CleanBrands Name: CleanRest PRO Max

Style: MicronOne B: Waterproof Breathable Sleep Surface Fabric

Color Optic White

VIRAL PENETRATION, RESISTANCE OF MATERIALS USED IN PROTECTIVE CLOTHING TO PENETRATION BY BLOODBORNE PATHOGENS (ASTM F1671), PROCEDURE B, USING NYLON MESH RETAINING SCREEN:

Viral penetration was tested for using a  $\phi$ X174 bacteriophage suspension for 60 minutes. At the end of the test, the observed side of the test sample was rinsed with sterile medium and assayed for the presence of  $\phi$ X174 bacteriophage.

### Executive Summary

Compatibility ratio for B tested in triplicate was 0.98 (i.e., exposure of virus to the test sample for 1 h did not affect the virus titer).

Settle plates (two from hood and two from bench) showed no plaques, indicating the absence of aerosol bacteriophage spread. Testing of test cells before exposure to virus was uniformly negative for virus showing the absence of test cell contamination.

			Test Cell Wash		
Test Article (each in triplicate)	pre-challenge (PFU <sup>a</sup> /ml)	post- challenge (PFU/ml)	(5ml) bacteriophage penetration (PFU/ml)	Visual penetration	Test Result
В	3.0 x 10 <sup>8</sup>	$3.3 \times 10^{8}$	0	No	Pass
Impermeable control	3.0 x 10 <sup>8</sup>	3.0 x 10 <sup>8</sup>	0	No	Pass
Permeable control	3.0 x 10 <sup>8</sup>	3.0 x 10 <sup>8</sup>	>200	Yes	Fail (expected)

a PFU: plaque-forming units

18 M Con Thi

Laboratory Manager

JG/04...JG/04

Sested & Engluded

Sested & Engluded

Sested & Engluded

Stacy Sadowy

Quality Assurance Manager

Page 2 of 2

All of the tests in this report were carried out in accordance with the procedures and provisions detailed in the Vartest Quality Assurance Manual. Vartest maintains a quality system in compliance with ISO/IEC 17025:2005. The findings and results in this test report apply only to the specific sample(s) submitted to by the client for testing.